

Amendments to the Claims

The listing of claims replaces all prior versions, and listings, of claims in the application.

Listing of claims:

1. (Currently amended) A method of fabricating a diffractive or non-dispersive polymer dispersed liquid crystal electrooptic device, comprising the steps of:

providing a non-chiral nematic liquid crystal in the form of a eutectic mixture,
wherein said nematic liquid crystal has a positive dielectric anisotropy;
providing a photo-curable pre-polymer mixture;

mixing said nematic liquid crystal with said photo-curable pre-polymer
mixture to form a homogeneous nematic/pre-polymer mixture, with said nematic
liquid crystal being greater than 40% (by weight) of said combined homogeneous
mixture;

providing a cell comprising a pair of spaced apart transparent substrates
that are each coated with a transparent conductive layer, without the inclusion of an
alignment layer for aligning said nematic liquid crystal;

filling said cell with said homogeneous nematic/pre-polymer mixture; and
photo-curing said nematic/pre-polymer mixture using a spatially
inhomogeneous illumination source; and

deriving said spatially inhomogeneous illumination source used to photo-cure the
nematic/pre-polymer mixture from the interference of two coherent optical beams
within said cell; and

utilizing the above fabrication method to create said diffractive or non-dispersive
electrooptic device in the form of a polymer dispersed liquid crystal (PDLC)
exhibiting low scattering loss and high index modulation.

2. (Canceled)

3. (Canceled)

4. (Previously amended) The method as defined in claim 1 wherein said substrates are separated from about 5 μm to about 20 μm .

5. (Original) The method as defined in claim 1 wherein said PDLC is comprised of a dispersion of discrete droplets containing nematic liquid crystal-rich material in a polymer-rich matrix.

6. (Original) The method as defined in claim 1 wherein said PDLC is comprised of regions of inter-connected spaces that are filled with nematic liquid crystal-rich material.

7. (Canceled)

8. (Currently amended) The method as defined in claim 7 1 wherein said coherent optical beams each have a wavelength in the ultraviolet spectrum.

9. (Currently amended) The method as defined in claim 7 1 wherein said interfering optical beams are incident symmetrically about a direction normal to said cell in order to form said PDLC as an unslanted PDLC transmission grating.

10. (Original) The method as defined in claim 9 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a grating period that is greater than half the wavelength of the light to be diffracted by the PDLC transmission grating during use of said transmission grating.

11. (Previously amended) The method as defined in claim 9 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a spatial frequency that is sufficiently high to prohibit propagating diffracted orders for normal incident light, thereby creating an electrooptic retarder with electrically tunable birefringence.

12. (Original) The method as defined in claim 10 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high degree of orientational order and has its nematic director substantially aligned along its grating vector when no drive field is applied across said cell.

13. (Previously amended) The method as defined in claim 6 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high degree of orientational order and has its nematic director substantially aligned along its grating vector when no drive field is applied across said cell.

14. (Currently amended) A method of fabricating a diffractive or non-dispersive polymer dispersed liquid crystal static optical device, comprising the steps of:

providing a non-chiral nematic liquid crystal in the form of a eutectic mixture,
wherein said nematic liquid crystal has a positive dielectric anisotropy;
providing a photo-curable pre-polymer mixture;

mixing said nematic liquid crystal with said photo-curable pre-polymer mixture to form a homogeneous nematic/pre-polymer mixture, with said nematic liquid crystal being greater than 40% (by weight) of said combined homogeneous mixture;

providing a cell comprising a pair of spaced apart transparent substrates, without the inclusion of an alignment layer for aligning said nematic liquid crystal;

filling said cell with said homogeneous nematic/pre-polymer mixture; and
photo-curing said nematic/pre-polymer mixture using a spatially inhomogeneous illumination source; and

deriving said spatially inhomogeneous illumination source used to photo-cure the nematic/pre-polymer mixture from the interference of two coherent optical beams within said cell; and

utilizing the above fabricating method to create said diffractive or non-dispersive static optical device in the form of a polymer dispersed liquid crystal (PDLC) exhibiting low scattering loss and high index modulation.

15. (Previously amended) The method as defined in claim 14 wherein said substrates are separated from about 5 μm to about 20 μm .

16. (Original) The method as defined in claim 14 wherein said PDLC is comprised of a dispersion of discrete droplets containing nematic liquid crystal-rich material in a polymer-rich matrix.

17. (Original) The method as defined in claim 14 wherein said PDLC is comprised of regions of inter-connected spaces that are filled with nematic liquid crystal-rich material.

18. (Canceled)

19. (Currently amended) The method as defined in claim ~~18~~ 14 wherein said coherent optical beams each have a wavelength in the ultraviolet spectrum.

20. (Currently amended) The method as defined in claim ~~18~~ 14 wherein said interfering optical beams are incident symmetrically about a direction normal to said cell in order to form said PDLC as an unslanted PDLC transmission grating.

21. (Original) The method as defined in claim 20 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a grating period that is greater than half the wavelength of the light to be diffracted by the PDLC transmission grating during use of said transmission grating.

22. (Original) The method as defined in claim 20 wherein said optical beams interfere at such an angle as to form said unslanted PDLC transmission grating with a spatial frequency that is sufficiently high to prohibit propagating diffracted orders for normal incident light, thereby creating a retarder with electrically tunable birefringence.

23. (Previously amended) The method as defined in claim 16 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high degree of orientational order and has its nematic director substantially aligned along its grating vector.

24. (Previously amended) The method as defined in claim 17 where said nematic liquid crystal in the nematic-rich regions in the PDLC contains a high degree of orientational order and has its nematic director substantially aligned along its grating vector.

25. (Canceled)